

DURALLOY™

THERMOPLASTIC COATINGS

Wire goods are found in many products that we use on a daily basis. Their coating require special attention to make sure it is hard wearing and tough, to extend the product lifetime and overall durability.

DURALLOY™ is one-coat thermoplastic coating solution that is designed specifically for the finishing of wire goods.



OVERVIEW

How does it **work**?

DURALLOY™ is formulated with plasticizer for flexibility and hardness. It adheres as a single coat.

Main Features

- One coat system.
- Corrosion and chemical resistance.
- Excellent durability.

TYPICAL APPLICATIONS

Architectural

- Fencing & Railing
- Street Furniture

COLOR OPTIONS

Stock colors

Select one of the many stock colors that are readily available for processing.

Color reference chart

Get inspired from a broad range of standard colors. Request a RAL fan deck or ask one of our experts

Custom formulations

Talk to your coating expert regarding custom formulations to fit your exact needs.

SUPPORT

Compliance

DURALLOY™ can be formulated to be compliant with certain guidelines. Ask our experts to see what different types of compliance, certification, or accreditation is available in your area.

Care & maintenance

To ensure the life of your asset is maximised, a simple and regular maintenance program should be implemented.

Contact our experts for specific tips and advice of cleaning.

Troubleshooting

We stand by our products, even when things don't go quite as planned. From cleaning and phosphating all the way to the final cured film appearance, we are here to help address your issues with proven solutions.

Contact our experts for tailored support.

PROVEN PERFORMANCE

TYPE	METHOD	RESULT
RECOMMENDED THICKNESS	ASTM D6132	8 mils (203 micron) - 12 mils (305 micron)
GLOSS	ASTM D523	70 ± 5
HARDNESS	ASTM D2240	Shore D 35 ± 5
TENSILE STRENGTH	ASTM D638	2600 psi (18 MPa)
ELONGATION (%)	ASTM D638	180%
BRITTLENESS TEMPERATURE		-4 °F (-20 °C)
FLEXIBILITY	ASTM D522	1/8 in (3.2 mm), no cracks (>32%) (Conical Mandrel)
SALT SPRAY	ASTM B117	500 hrs. No significant under cut or creep
QUV	ASTM G53	150 hrs, No significant change in color or gloss.
HUMIDITY RESISTANCE	ASTM D2247	No blistering or loss of gloss after 1000 hours.



FORMULATING THE RIGHT MIX

For more than 45 years, the Protech Group has been developing and manufacturing coatings, paints, and specialty materials. Through quality and innovation, we formulate the right mix to protect and enhance what matters most to our customers. The Protech Group products are manufactured in more than 20 sites worldwide. We serve our customers in countless markets and industries, including construction, infrastructure, transportation, consumer goods, and healthcare.



AMERICAS
americas@protechpowder.com

ASIA-PACIFIC
asia@protechpowder.com

**EUROPE, MIDDLE EAST
& AFRICA (EMEA)**
emea@protechpowder.com